



display distribution

Caratteristiche Tecniche

	POF Shrink Film			Cross-Linked Shrink Film			Antifog Cross-Link Shrink Film		
Thickness (micron)	12	15	19	12	15	19	12	15	19
Yield (m ² /kg)	91	72.8	57.4	90.6	72.5	57.1	90.3	72.3	56.9
Folded Length (mm)	1667	1331	1067	1667	1331	1067	1667	1331	1067
Folded Film Width (Fascia) (mm)	200 - 800			200 - 800			200 - 800		
Tensile Strength (n/mm ²)	125 - 120	120 - 100	125 - 120	125 - 115	120 - 100	125 - 105	125 - 115	120 - 100	125 - 105
Elongation (%)	105 - 100	105 - 100	110 - 105	105 - 100	105 - 100	110 - 107	105 - 100	105 - 100	110 - 108
Seal Strength (n/mm ²)	40	40	39	71	67	65	71	67	65
Shrink at 120" (%)	52 - 54	52 - 53	52 - 53	70 - 71	68 - 69	67 - 67	70 - 71	68 - 69	67 - 67
Shrink at 130" (%)	64 - 67	63 - 66	62 - 65	82 - 83	82 - 82	80.5 - 81	82 - 83	81 - 82	80 - 81